



INSTRUCTIONS 1008-G00 e

Section	1008
Effective	May 2007
Replaces	February 2005

CHEMICAL COMPATIBILITY OF TVP



Z.I. La Plaine des Isles - F 89000 AUXERRE - FRANCE
Tel. : +33 (0)3.86.49.86.30 - Fax : +33 (0)3.86.49.87.17
contact@mouvex.com - www.mouvex.com

Your distributor :

CHEMICAL COMPATIBILITY OF TVP



HIGH PERFORMANCE PEEK™ POLYMERS

VICTREX® PEEK™ POLYMER

CHEMICAL RESISTANCE

CHEMICAL	73°F (23°C)	212°F (100°C)	392°F (200°C)
ACIDS			
Acetic Acid, 10% Conc.	A	A	
Acetic Acid, Conc.	A	A	A
Acetic Acid, Glacial	A	A	
Acrylic Acid	A	A	
Aqua Regia	C	C	C
Benzene Sulfonic Acid	C		
Benzoic Acid	A	A	
Boric Acid	A	A	
Carbolic Acid	A		
Carbonic Acid	A	A	
Chloroacetic Acid	A	A	
Chlorosulfonic Acid	C	C	C
Chromic Acid, 40% Conc.	A		
Chromic Acid, Conc.	C	C	C
Citric Acid	A	A	
Formic Acid	B	B	
Hydrobromic Acid	C	C	C
Hydrochloric Acid, 10% Conc.	A	A	
Hydrochloric Acid, Conc.	A	B	
Hydrocyanic Acid	A	A	
Hydrofluoric Acid, 40% Conc.	C	C	C
Lactic Acid	A	A	
Maleic Acid	A	A	
Nitric Acid, 10% Conc.	A	A	
Nitric Acid, 30% Conc.	B		
Nitric Acid, 50% Conc.	C	C	C
Nitric Acid, Conc.	C	C	C
Nitrous Acid, 10%	A		
Oleic Acid	A		
Oleum	C	C	C
Oxalic Acid	A	A	
Perchloric Acid	A	A	
Phosphoric Acid, 10% Conc.	A	A	A
Phosphoric Acid, 50% Conc.	A	A	A
Phosphoric Acid, 80% Conc.	A	A	
Phthalic Acid	A	A	
Picric Acid	A	A	
Silicic Acid	A	A	
Sulfuric Acid, <40% Conc.	B	B	B
Sulfuric Acid, >40% Conc.	C	C	C
Sulfurous Acid	A	A	
Tannic Acid, 10% Conc.	A	A	
Tartaric Acid	A	A	
Trifluoromethyl Sulfonic Acid	C	C	C

CHEMICAL	73°F (23°C)	212°F (100°C)	392°F (200°C)
ALCOHOLS			
Benzyl Alcohol	A		
Butanol	A		
Cyclohexanol	A		
Ethanol	A	A	
Ethylene Glycol	A	A	B
Ethylene Glycol, 50% Conc.	A	A	A
Glycerol	A		
Gylcols	A	A	
Isopropanol	A		
Methanol	A	A	
Propanol	A		
ALDEHYDES/KETONES			
Acetaldehyde	A	A	
Acetone	A	A	
Benzaldehyde	A		
Cyclohexanone	A		
Formaldehyde	A	A	
Formalin	A		
Ketones	A		
Methylethyl Ketone (MEK)	A	B	C
N-Methyl-2-Pyrrolidone (NMP)	A		
BASES			
Ammonia 880	A		
Ammonia Anhydrous	A	A	A
Ammonia Liquid	A	A	A
Ammonium Hydroxide, 10% Conc.	A		
Ammonium Hydroxide, Conc.	A		
Calcium Hydroxide	A		
Hydrazine	A	A	
Hydroxides	A		
Magnesium Hydroxide	A		
Potassium Hydroxide, 10% Conc.	A		
Potassium Hydroxide, 70% Conc.	A		
Sodium Hydroxide, 10% Conc.	A	A	A
Sodium Hydroxide, 50% Conc.	A	A	A
Sodium Hydroxide, Conc.	A		
ESTERS			
Aliphatic Esters	A	A	
Amyl Acetate	A	A	
Butyl Acetate	A		
Dibutyl Phthalate	A		
Dimethyl Phthalate	A		
Diocetyl Phthalate	A		
Ethyl Acetate	A		

See key on back

CHEMICAL COMPATIBILITY OF TVP (continued)

VICTREX® PEEK™ POLYMER

CHEMICAL	73°F (23°C)	212°F (100°C)	392°F (200°C)	CHEMICAL	73°F (23°C)	212°F (100°C)	392°F (200°C)
ESTERS (cont.)				HYDROCARBONS (cont.)			
Oils (Di-Ester and Phosphate Ester Based)	A	A		Kerosene	A		
ETHERS				Lubricating Oil	A		
Diethylether	A	A		Methane (Gas)	A	A	A
Dioxane	A			Motor Oil	A		A
Ether	A	A		Naphtha	A	A	
Ethylene Oxide (EtO)	A			Naphthalene	A	A	
Tetrahydrofuran (THF)	A			Oils (Petroleum)	A	A	
HALOGENATED ORGANICS				Oils (Vegetable)	A	A	
1,1,1 Trichloroethane (Genklene*)	A			Pentane	A		
1,2 Dichloroethane	A			Petroleum Ether	A		
Carbon Tetrachloride	A	A		Propane	A		
Chorobenzene	A	A		Skydrol* Hydraulic Fluid	A		
Chloroform	A	A		Styrene (Liquid)	A		
Dibromoethane	A			Toluene	A		
Dichlorobenzene	A			Transformer Oil	A	A	
Dichloroethane	A			Vaseline*	A		
Ethylene Dichloride	A			Xylene	A		
Freon* 11 Trichlorofluoromethane	A			INORGANICS			
Freon 113 Trichlorotrifluoroethane	A			Aluminum Chloride	A	A	
Freon 114 1,1 Dichloro 1,2,2,2 Tetrafluoroethane	A			Aluminum Sulfate	A	A	
Freon 12 Dichlorodifluoromethane	A			Alum, Saturated	A	A	
Freon 22 Chlorodifluoromethane	A	A		Ammonium Chloride, 10% Conc.	A	A	
Freon 134a	A			Ammonium Nitrate	A	A	
Freon 502	A	A		Antimony Trichloride	A	A	
Methylene Chloride	A			Barium Salts (Chloride, Sulfide)	A		
Perchloroethylene	A	A		Bleach	A	A	
Trichloroethylene	A	A		Brine	A	A	
HYDROCARBONS				Bromine	C	C	C
Acetylene	A	A		Bromine (Dry)	C	C	C
Aromatic Solvents	A	A		Bromine (Wet)	C	C	C
Aviation Hydraulic Fluid	A			Bromine Water, Saturated	A	A	
Benzene	A	A		Calcium Bisulfide	A	A	
Brake Fluid (Mineral)	A	A	A	Calcium Carbonate	A		
Brake Fluid (Polyglycol)	A	A	A	Calcium Chloride	A	A	
Butane	A			Calcium Hypochlorite	A	A	
Crude Oil	A			Calcium Nitrate	A		
Cyclohexane	A	A		Calcium Sulfate	A	A	
Diesel Oil	A			Carbon Dioxide (Dry)	A		
Dowtherm* A			C	Carbon Monoxide (Gas)	A	A	A
Dowtherm G			B	Chlorine	C	C	C
Dowtherm HT			B	Copper Acetate	A	A	
Dowtherm LF			B	Copper Carbonate	A	A	
Ethane	A			Copper Chloride	A	A	
Fuel Oil	A			Copper Cyanide	A	A	
Gas (Manufactured)	A			Copper Fluoride	A	A	
Gas (Natural)	A			Copper Nitrate	A	A	
Gasoline	A	A		Copper Sulfate	A	A	
Heptane	A			Cupric Fluoride	A	A	
Hexane	A			Cupric Sulfate	A	A	
Hydraulic Fluid	A			Cuprous Chloride	A	A	
Iso-Octane	A			Ethylene Nitrate	A		
				Ferric Chloride	B	B	
				Ferric Nitrate	A		
				Ferric Oxide	A	A	

See key on back

CHEMICAL COMPATIBILITY OF TVP (continued)

CHEMICAL RESISTANCE

CHEMICAL	73°F (23°C)	212°F (100°C)	392°F (200°C)	CHEMICAL	73°F (23°C)	212°F (100°C)	392°F (200°C)
INORGANICS (cont.)				INORGANICS (cont.)			
Ferric Sulfate	A			Sodium Sulfite	A	A	
Ferrous Chloride	A			Sodium (Hot)	C	C	C
Ferrous Nitrate	A			Stannic Chloride	A	A	
Ferrous Sulfate	A	A		Stannous Chloride	A	A	
Fluorine	C	C	C	Steam	A	A	A
Hydrogen Peroxide	A	A		Sulfites	A	A	
Hydrogen Sulfide (Gas)	A	A	A	Sulfur	A	A	
Iodine	B			Sulfur Chloride	A	A	
Lead Acetate	A	A		Sulfur Dichloride	A	A	
Lime	A	A		Sulfur Dioxide	A	A	A
Magnesium Chloride	A	A		Sulfur Hexafluoride (Gas)	A		
Magnesium Sulfate	A	A		Sulfur Trioxide	A	A	
Mercuric Chloride	A	A		Tar	A		
Mercurous Chloride	A			Tetraethyl Lead	A		
Mercury	A	A		Water, Distilled	A	A	
Nickel Acetate	A	A		Water	A	A	A
Nickel Chloride	A	A		Water, Sea/Salt	A	A	
Nickel Nitrate	A	A		Zinc Chloride	A	A	
Nickel Salts	A			Zinc Sulfate	A	A	
Nickel Sulfate	A	A		MISCELLANEOUS			
Nitrogen	A			Adhesives (not cyanoacrylates)	A		
Nitrous Oxide	A			Apple Juice	A		
Oxygen	A			Aviation Spirit	A		
Ozone	A	B		Beer	A	A	
Phosphorous Chlorides	A	A		Cooking Oil	A		
Phosphorous Pentoxide	A	A		Creosote	A		
Potassium Aluminum Sulfate	A	A		Detergent Solutions (non-phenolic)	A	A	
Potassium Bicarbonate	A			Edible Fats & Oils	A		
Potassium Bromide	A	A		Fatty Acids	A	A	
Potassium Carbonate	A			Fruit Juice	A	A	
Potassium Chlorate	A	A		Gelatin	A	A	
Potassium Chloride	A	A		Ketchup	A		
Potassium Dichromate	A			Linseed Oil	A		
Potassium Ferricyanide	A			Milk	A	A	
Potassium Ferrocyanide	A			Mineral Oil	A		
Potassium Hydroxide	A	A		Molasses	A	A	
Potassium Nitrate	A	A		Olive Oil	A	A	
Potassium Permanganate	A			Peanut Oil	A	A	
Potassium Sulfate	A	A		Paraffin	A	A	
Potassium Sulfide	A			Sewage	A	A	
Silicone Fluids	A	A		Soap Solution	A		
Silver Nitrate	A	A		Starch	A	A	
Sodium Acetate	A			Tallow	A	A	
Sodium Bicarbonate	A			Turpentine	A		
Sodium Carbonate	A	A		Urea	A	A	
Sodium Chlorate	A	A		Varnish	A		
Sodium Chloride	A	A		Vinegar	A	A	
Sodium Hypochlorite	A	A		Wax	A		
Sodium Nitrate	A	A		White Spirit	A		
Sodium Nitrite	A			Wines and Spirits	A		
Sodium Peroxide	A	A		Yeast	A	A	
Sodium Salts	A						
Sodium Silicate	A	A					
Sodium Sulfate	A	A					
Sodium Sulfide	A	A					

See key on back

CHEMICAL COMPATIBILITY OF TVP (continued)



CHEMICAL RESISTANCE

CHEMICAL	73°F (23°C)	212°F (100°C)	392°F (200°C)
ORGANO-NITROGENS			
Acetonitrile	A		
Aniline	A	B	
Dimethyl Formamide (DMF)	A		
Diethylamine	A		
Nitrobenzene	A		C
Pyridine	A	A	
PHENOLS			
Phenol (Conc.)	C	C	C
Phenol (Dilute)	A		
SULFUR COMPOUNDS			
Carbon Disulfide	A	A	
Dimethylsulfoxide (DMSO)	B	B	
Diphenylsulfone (DPS)	B	C	C
Ethylene Sulfate	A		

KEY

- A — No attack. Little or no absorption.
- B — Slight attack. Satisfactory use of VICTREX PEEK will depend on the application.
- C — Severe attack. VICTREX PEEK should not be used for any application where these chemicals are present.

Dowtherm is a registered trademark of Dow Chemical
 Skydrol is a registered trademark of Monsanto
 Genklene is a registered trademark of ICI
 Freon is a registered trademark of DuPont
 Vaseline is a registered trademark of Chesebrough-Pond's, Inc.

World Headquarters

Victrex plc
 Hillhouse International
 Thornton Cleveleys
 Lancashire FY5 4QD
 United Kingdom
 Tel: +44 (0) 1253 897700
 Fax: +44 (0) 1253 897701
 Email: victrexplc@victrex.com

Americas

Victrex USA Inc
 3A Caledon Court
 Greenville SC 29615
 USA
 Tel: + (1) 800 VICTREX
 Tel: + (1) 864 672 7335
 Fax: + (1) 864 672 7328
 Email: usasales@victrex.com

Europe

Victrex Europa GmbH
 Hauptstr. 11
 65719 Hofheim/Ts.
 Germany
 Tel: + (49) 6192 964949
 Fax: + (49) 6192 964948
 Email: eurosales@victrex.com

Asia-Pacific

Victrex-MC Inc
 Hanai Building 6F
 1-2-9 Shiba Kouen
 Minato-ku
 Tokyo 105 -0011
 Japan
 Tel: +(81) 35777 8737
 Fax: +(81) 35777 8738
 Email: asiapacificsales@victrex.com

Victrex plc believes that the information contained in this brochure is an accurate description of the typical characteristics and/or uses of the product or products, but it is the customer's responsibility to thoroughly test the product in his specific application to determine its performance, efficacy and safety for each end-use product, device or other application. Suggestions of uses should not be taken as inducements to infringe any particular patent. The information and data contained herein are based on information we believe reliable. Mention of a product in this documentation is not a guarantee of availability. Victrex plc reserves the right to modify products, specifications and/or packaging as part of a continuous program of product development.



www.victrex.com